

OPAN SPUN YARN				
TYPE	10s/2	20s/2	30s/2	40s/1
Count(tex)	120	60	41	14.5
Breaking load(cN)	900	480	310	150
Tenacity(cN/tex)	7.5	8	7.4	10.3
Elongation(%)	11	12	11	10
Twist(tpm)	560	900	850	97.3